






















TECHNICAL CHARACTERISTICS

ambra			wineo	
Covering type according to EN ISO 10582: Heterogeneous resilient-flooring to glue				
	ambra wood	ambra stone		
Format	1200 x 180 mm	609.6 x 304.8		
Product thickness	2 mm	2 mm		
Planks, tiles / m² per box	18 / 3.89 m ²	18 / 3.34 m ²		
Boxes / m² per pallet	60 / 233.40 m ²	72 / 240.48 m ²		
Guarantee	15 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de			
Classification				
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices	1	Surface sealing
	Utilization class 31 Medium use in the commercial sector EN ISO 10874	Hotel rooms, small offices	2	Surface texture various embossings
	Wear layer binder content EN ISO 10582	Type I	3	Wear layer Thickness 0.3 mm
	Wear resistance EN 660-2	Group T acc. to DIN EN 649:2011-05	4	Decor Decor film
	Reaction to fire EN 13501-1	B _{fl} - s1	5	Base layer
	Anti slip category DIN 51130	R 9	6	Backing
	Slip resistance EN 13893	μ ≥ 0.30 - DS	DESIGN FLOORING to glue 	
	Anti-static properties EN 1815	≤ 2 kV	Certifications	
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	 <p>windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf - 07 - Elastischer Bodenbelag DOP: 0401001 EN 14041:2004 Resilient Flooring to be used within a building.</p>  <p>ÉMISSIONS DANS L'AIR INTÉRIEUR A+ Informations représentatives des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité pour l'habitation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p>  <p>Schadstoffgeprüft Emissionsgeprüft PROFI</p>  <p>factory made coated</p>	
	Light fastness EN ISO 105-B02	≥ 6		
	Residual indentation EN ISO 24343-1	~ 0.02 mm		
	Castor chair test EN 425 / ISO 4918	Type W – no visible change		
	Thermal resistance EN 12667	~ 0.01 (m ² K)/W		
	Impact sound reduction EN ISO 16251-1	~ 4 dB		
	Dimension stability EN ISO 23999	~ 0.15 %		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.