

Mammut

Technical details		Unit	Test method
Production method	1/10" Loop pile		
Pile material	1005 Polypropylene		
Width	400	cm	
Carrier	Woven		
Backing	Action back		
Effective pile height	Ca. 2,4	mm	ISO 1766
Total Thickness	Ca. 5,1	mm	ISO 1765
Pile weight	Ca. 600	g/m ²	
Total weight	Ca. 1730	g/m ²	ISO 8543
Pile density	Ca. 0,147	g/cm ³	
Number of tufts	Ca. 259.000	m ⁻²	ISO 1763
Electrical resistance horizontal	≤ 10 ¹³ ??	Ω	
Electrical resistance vertical	≤ 10 ¹³ ??	Ω	
Noise insulation	Ca. 8	dB	ISO 717-2:2013
Noise absorption	0,15	α _w	ISO 354:2003
Thermal resistance	0,057	m ² KW	ISO 8302:1991
Lightfastness	7-8		ISO 105-B02:2013
Rubfastness	4-5		ISO 105-X12:2002
Water resistance	5		ISO 105-E01:2013
Reaction to fire	Cfl-S1		EN 13501-1:2007
Classification	23 & 33		
Comfort class	LC1		
Castor chair	Occasional use		
Stair suitability	Occasional use		
Guarantee	7 year		

