






















TECHNICAL CHARACTERISTICS

ambra			wineo	
Covering type according to EN ISO 10582: Heterogeneous resilient-flooring for glueless installation				
	ambra wood	ambra stone		
Format	1212 x 185 mm	600 x 314 mm		
Product thickness	4.5 mm	4.5 mm		
Planks, tiles / m² per box	10 / 2.24 m ²	12 / 2.26 m ²		
Boxes / m² per pallet	52 / 116.48 m ²	52 / 117.52 m ²		
Guarantee	15 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de			
Classification				
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices	1	Surface sealing
	Utilization class 31 Medium use in the commercial sector EN ISO 10874	Hotel rooms, small offices	2	Surface texture various embossings
	Wear layer binder content EN ISO 10582	Type I	3	Wear layer Thickness 0.3 mm
	Wear resistance EN 660-2	Group T acc. to DIN EN 649:2011-05	4	Decor Decor film
	Reaction to fire EN 13501-1	B _{fl} - s1	5	Base layer with glass fibre reinforced
	Anti slip category DIN 51130	R 9	6	Profile connection Connect technology 
	Slip resistance EN 13893	μ ≥ 0.30 – DS	7	Backing
	Anti-static properties EN 1815	≤ 2 kV	Insulation mat silentCOMFORT (seperately available)	
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	Bevelled edge – ambra wood	
	Light fastness EN ISO 105-B02	≥ 6	Certifications	
	Residual indentation EN ISO 24343-1	~ 0.07 mm	   	
	Castor chair test EN 425 / ISO 4918	Type W – no visible change		
	Thermal resistance EN 12667	~ 0.033 (m ² K)/W ~ 0.0254 (m ² K)/W in combination with silentCOMFORT		
	Impact sound reduction EN ISO 16251-1	~ 7 dB up to 14 dB in combination with silentCOMFORT		
	Dimension stability EN ISO 23999	~ 0.1 %		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.