























TECHNICAL CHARACTERISTICS

wineo 600				wineo		
Covering type according to EN ISO 10582: Heterogeneous resilient-flooring to glue						
	wineo 600 wood	wineo 600 wood XL	wineo 600 stone	wineo 600 stone XL		
Format	1200 x 180 mm	1505 x 235 mm	609,6 x 304.8 mm	900 x 450 mm		
Product thickness	2 mm	2 mm	2 mm	2 mm		
Planks, tiles / m² per box	18 / 3.89 m ²	12 / 4.24 m ²	18 / 3.34 m ²	12 / 4.86 m ²		
Boxes / m² per pallet	60 / 233.40 m ²	64 / 271.36 m ²	72 / 240.48 m ²	50 / 243.00 m ²		
Guarantee	20 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de					
Classification					Product composition	
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices		1	Surface sealing	
	Utilization class 32 Normal use in the commercial sector EN ISO 10874	Offices, boutiques, cafés		2	Surface texture various embossings	
	Utilization class 41 Medium use in the light industrial sector EN ISO 10874	Workshop for precision mechanics		3	Wear layer Thickness 0.4 mm	
	Wear layer binder content EN ISO 10582	Type I		4	Decor Decor film	
	Wear resistance EN 660-2	Group T acc. to DIN EN 649:2011-05		5	Base layer	
	Reaction to fire EN 13501-1	B _{fl} - s1		6	Backing	
	Anti slip category DIN 51130	R 9			DESIGN FLOORING to glue 	
	Slip resistance EN 13893	$\mu \geq 0.30$ - DS			Certifications	
	Anti-static properties EN 1815	≤ 2 kV			 <p>windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf</p> <p>- 07 -</p> <p>Elastischer Bodenbelag DOP: 0401001 EN 14041:2004</p>  <p>Resilient Flooring to be used within a building.</p>  <p>ÉMISSIONS DANS L'AIR INTÉRIEUR A+ A B C</p> <p>Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p>  <p>Schadstoffgeprüft Emissionsgeprüft</p>  <p>factory made coated</p>	
	Light fastness EN ISO 105-B02	≥ 6				
	Residual indentation EN ISO 24343-1	~ 0.02 mm				
	Castor chair test EN 425 / ISO 4918	Type W – no visible change				
	Thermal resistance EN 12667	~ 0.01 (m ² K)/W				
	Impact sound reduction EN ISO 16251-1	~ 4 dB				
	Dimension stability EN ISO 23999	~ 0.15 %				
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203				
Relevant information:						
<ul style="list-style-type: none"> • Installation in utilization class 41 possible (vehicular traffic excluded). • Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C. • Cleaning and care: see separate cleaning & care instruction. • Technical subjects can be changed by windmüller flooring products WFP GmbH. 						