TECHNICAL SPECIFICATION



CONSTRUCTION MACHINE GAUGE

1/8th Gauge Cut Pile Twist

FLITE

1/8th Gauge Cut Pile Twist

PILE HEIGHT TUFT DENSITY

ISO 1766 7.5 mm ISO 1763 120,900 tufts/m² 9.1 mm 127,100 tufts/m²

PILE WEIGHT

1.526 ams/m² 45 oz/yd²

1.865 ams/m² 55 oz/yd² 2,802 gms/m²

DELUXE

TOTAL CARPET WEIGHT **CARPET THICKNESS** WIDTH

ISO 8543 ISO 1765

2,463 gms/m² 10.6 mm 4 & 5 metre

12.3 mm 4 & 5 metre



COMPOSITION

PILE CONTENT PRIMARY BACKING SECONDARY BACKING ISO 1833 80% Wool, 10% Nylon, 10% Tuftbond Polyester

Woven Polypropylene Woven Secondary

80% Wool, 10% Nylon, 10% Tuftbond Polyester

Woven Polypropylene Woven Secondary



PERFORMANCE

SUITABILITY WIRA ABRASION TEST STATIC LOADING DYNAMIC LOADING

TUFT ANCHORAGE

PD 6527: Clause 17 ISO 3416 ISO 2094

ISO 4919

Extra Heavy Domestic Exceeds 23 100 Rubs

22.1% Thickness Loss after 24 hrs recovery 30.6% Thickness Loss after 1,000 impacts Above 1 ka

Extra Heavy Domestic / Medium Contract

Exceeds 25 300 Rubs

19.5% Thickness loss after 24 hrs recovery 29.5% Thickness loss after 1,000 impacts Above 1 ka



COLOUR FASTNESS

LIGHT FASTNESS WET FASTNESS SHAMPOO FASTNESS ISO 105-B02 ISO 105-E01 BS 1006: UK-TB 5 on all colours 4 on all colours 4/5 on all colours

5 on all colours 4/5 on all colours 4/5 on all colours



THERMAL VALUE

TOG VALUE THERMAL RESISTANCE ISO 5085-1 1.6 Tog $0.16 \, \text{m}^2 \, \text{k/w}$ 2.0 Tog $0.2 \, m^2 \, k/w$



FLAMMABILITY

CE MARK RATING Dfl, S1

HOT METAL NUT TEST BS4790

METHENAMINE PILL TEST ISO 6925

Pass - Low radius of ignition Pass - Low radius of ignition

Pass



CHEMICAL IMPACT

FORMALDEHYDE

 $C \in$ Εī

Pass

C€

Εī



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT

Eulan Treated

Eulan Treated



ANTI STATIC

-0.2 kv (Requirement less than +2.0kv)

-0.4 kv (Requirement less than +2.0kv)

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.